

205.2 - Fission Track Glass (wafer form)

This SRM, which contains uranium, will aid laboratories performing fission track analyses in interlaboratory comparisons of data and in monitoring neutron fluences. The material was irradiated in the 20MW reactor at the NIST Center for Neutron Research, at two different neutron energies. Each unit consists of four unirradiated glass wafers and two irradiated wafers.

Technical Contact: david.gilliam@nist.gov

PLEASE NOTE: The tables are presented to facilitate comparisons among a family of materials to help customers select the best SRM for their needs. For specific values and uncertainties, the certificate is the only official source.

SRM	963a
Description	Fission Track Glass U-1 mg/g
Unit of Issue	(set (6))
Neutron Fluence	
Uranium Composition (in mg/kg)	0.823
Uranium-235 (in Atom %)	0.2792
Reactor Position	RT-4: (10 ¹⁴ n/cm ²) RT-3: (10 ¹⁴ n/cm ²)
Neutron Fluence Copper Foil	39.5 41.2
Neutron Fluence Gold Foil	43.0 45.8